

SPONSOR: **Frasch**
Grand Prairie, TX

Sound Absorption
RAL™-A26-327

CONDUCTED: 2026-06-16

Page 1 of 8

ON: Skinny Baffle (8") in seven rows of three objects each, rows spaced 18" on center, objects in each row spaced 1" apart

TEST METHODOLOGY

Riverbank Acoustical Laboratories™ is accredited by the U.S. Department of Commerce, National Institute of Standards and Technology (NIST) under the National Voluntary Laboratory Accreditation Program (NVLAP) as an ISO 17025:2017 Laboratory (NVLAP Lab Code: 100227-0) and for this test procedure. The test reported in this document conformed explicitly with ASTM C423-23: "Standard Test Method for Sound Absorption and Sound Absorption Coefficients by the Reverberation Room Method." The specimen mounting was performed according to ASTM E795-23: "Standard Practices for Mounting Test Specimens During Sound Absorption Tests." A description of the measurement procedure and room specifications are available upon request. The results presented in this report apply to the sample as received from the test sponsor.

INFORMATION PROVIDED BY SPONSOR

The test specimen was designated by the sponsor as Skinny Baffle (8") in seven rows of three objects each, rows spaced 18" on center, objects in each row spaced 1" apart. The following nominal product information was provided by the sponsor prior to testing. The accuracy of such sponsor-provided information can affect the validity of the test results.

Product Under Test

Product Name: Skinny Baffle (8")
Manufacturer: Frasch

SPECIMEN MEASUREMENTS & TEST CONDITIONS

Through a full external visual inspection performed on the test specimen, Riverbank personnel verified the following information:

Test Specimen

Product Type: Baffles
Dimensions: 21 baffles @ 200 mm (7.875 in.) by 1200 mm (47.25 in.)
Thickness: 9.07 mm (0.357 in.)
Overall Weight: 14.29 kg (31.5 lbs)

Frasch
2026-06-16**RAL™-A26-327**
Page 2 of 8**SPECIMEN MEASUREMENTS & TEST CONDITIONS (continued)****Physical Measurements (per object)**

Dimensions: 0.2 m (7.875 in) wide by 1.2 m (47.25 in) long

Thickness: 0.01 m (0.357 in)

Weight: 0.68 kg (1.5 lbs)

Test EnvironmentRoom Volume: 291.98 m³

Temperature: 24.0 °C ± 0.0 °C (Requirement: ≥ 10 °C and ≤ 5 °C change)

Relative Humidity: 58.8 % ± 1.0 % (Requirement: ≥ 40 % and ≤ 5 % change)

Barometric Pressure: 97.5 kPa (Requirement not defined)

Each sound absorbing object had an exposed surface area of 0.51 m² (5.44 ft²). The total exposed surface area of all sound-absorbing objects was 10.6 m² (114 ft²).

MOUNTING METHOD

Type JV-MOD Mounting: The specimen is an array of 21 spaced sound absorbing objects suspended from cables such that the closest face is located approximately 1219 mm (48 in.) from the horizontal test surface. This approximates the mounting method of a typical ceiling baffle installation. The objects were distributed in seven rows of three objects each, with rows spaced 457 mm (18 in.) on center, and objects in each row spaced 25 mm (1 in.) apart. The width of the installed object array was 3651 mm (143.75 in.) and the length of the installed object array was 2781 mm (109.5 in.). The area of extended continuous surface attributed to the object array was 11.9 m² (128 ft²).

Frasch
2026-06-16

RAL™-A26-327
Page 3 of 8




Figure 1 – Specimen mounted in test chamber



Figure 2 – Detail of specimen materials

Frasch
2026-06-16**RAL™-A26-327**
Page 4 of 8**TEST RESULTS**

The preferred presentation of sound absorption test results for arrays of spaced objects is sound absorption (m^2) per object and total sound absorption (m^2) at each one-third-octave band

ASTM C423-23 Appendix X2 allows calculation of sound absorption per m^2 (SA/m^2) based on the projected horizontal surface area attributable to an array of objects. The extended continuous surface area used in this calculation is to be determined using the following procedure:

$S_{\text{array}} = (w + w_1) \times (l + l_1)$ If the set of objects consists of a rectangular array of equal sized objects with equal space between each object in a row and equal space between rows. (ASTM E423-23 X.2.3.1)

Where:

S_{array} = area of extended continuous surface attributed to the test specimen, m^2

w = the measured width of the installed object array, in meters

w_1 = the space between objects in the array along the width, in meters

l = the measured length of the installed object array, in meters

l_1 = the space between objects in the array along the length, in meters

The sound absorption per m^2 (SA/m^2) is calculated based on the following formula:

$$\alpha_{\text{array}} = (A_2 - A_1)/S_{\text{array}}$$

Where:

α_{array} = sound absorption per m^2 (SA/m^2) of extended continuous surface, no units,

A_1 = absorption of the empty reverberation room, m^2 and

A_2 = absorption of the room after the specimen has been installed, m^2 .

S_{array} = area of extended continuous surface attributed to the test specimen, m^2

Frasch
2026-06-16

RAL™-A26-327
Page 5 of 8

TEST RESULTS (continued)

1/3 Octave Center Frequency (Hz)	Total Absorption		Absorption per Object		α_{array} (Sabins/ft ²) (SA/m ²)
	(m ²)	(Sabins)	(m ² / Object)	(Sabins / Object)	
100	0.21	2.27	0.01	0.11	0.02
** 125	0.40	4.28	0.02	0.20	0.03
160	0.73	7.83	0.03	0.37	0.06
200	1.07	11.53	0.05	0.55	0.09
** 250	1.56	16.78	0.07	0.80	0.13
315	2.39	25.69	0.11	1.22	0.20
400	2.80	30.12	0.13	1.43	0.24
** 500	2.92	31.39	0.14	1.49	0.25
630	3.62	38.91	0.17	1.85	0.30
800	4.38	47.12	0.21	2.24	0.37
** 1000	4.91	52.88	0.23	2.52	0.41
1250	5.81	62.53	0.28	2.98	0.49
1600	6.81	73.26	0.32	3.49	0.57
** 2000	7.66	82.40	0.36	3.92	0.64
2500	8.34	89.80	0.40	4.28	0.70
3150	8.58	92.40	0.41	4.40	0.72
** 4000	8.70	93.63	0.41	4.46	0.73
5000	8.95	96.30	0.43	4.59	0.75


Array-NRC 0.35 over 11.9 m² of extended continuous surface area

Array-SAA 0.37 over 11.9 m² of extended continuous surface area

Digitally signed by
Eric P. Wolfram
Date: 2026.07.14
10:46:29 -05'00'

Tested by 
Marc Sciaky
Senior Experimentalist

Report by 
Keith Kimberling
Test Engineer

Approved by 
Eric P. Wolfram
Laboratory Manager

Note: Sound absorption per m² (SA/m²), and therefore the reported Single Number Ratings, are highly dependent on the exact sample shape, size, spacing, and extended continuous surface area present in the test and subsequent calculations. Changes to any of these parameters will change the resulting values. These presented results are valid only for the specific configuration present in this test.



NVLAP LAB CODE 100227-0

RIVERBANK ACOUSTICAL LABORATORIES IS ACCREDITED BY NVLAP (LAB CODE 100227-0) FOR ACOUSTICAL TESTING SERVICES IN ACCORDANCE WITH ISO/IEC 17025:2017 AND FOR THIS PROCEDURE. THIS REPORT MUST NOT BE USED BY THE CLIENT TO CLAIM PRODUCT CERTIFICATION, APPROVAL, OR ENDORSEMENT BY RAL, NVLAP, NIST, OR ANY AGENCY OF THE U.S. GOVERNMENT.


THIS REPORT SHALL NOT BE MODIFIED WITHOUT THE WRITTEN APPROVAL OF RAL. THE RESULTS REPORTED APPLY ONLY TO THE SPECIFIC SAMPLE SUBMITTED FOR TESTING; RAL ASSUMES NO RESPONSIBILITY FOR THE PERFORMANCE OF ANY OTHER SAMPLE.

Frasch
2026-06-16

RAL™-A26-327
Page 6 of 8

SOUND ABSORPTION REPORT

Skinny Baffle (8") in seven rows of three objects each, rows spaced 18" on center, objects in each row spaced 1" apart



Array-NRC 0.35 over 11.9 m² of extended continuous surface area

Array-SAA 0.37 over 11.9 m² of extended continuous surface area

Frasch
2026-06-16

RAL™-A26-327
Page 7 of 8

APPENDIX A: Extended Frequency Range Data

Specimen: Skinny Baffle (8") in seven rows of three objects each, rows spaced 18" on center, objects in each row spaced 1" apart (See Full Report)

The following non-accredited data were obtained in accordance with ASTM C423-23, but extend beyond the defined frequency range of 100Hz to 5,000Hz. These unofficial results are representative of the RAL test environment only and intended for research & comparison purposes.

1/3 Octave Band Center Frequency	Total Absorption		Absorption per Object		α_{array} (Sabins/ft ²)
(Hz)	(m ²)	(Sabins)	(m ² / Object)	(Sabins / Object)	(SA/m ²)
31.5	-0.43	-4.66	-0.02	-0.22	-0.04
40	0.42	4.50	0.02	0.21	0.04
50	0.13	1.37	0.01	0.07	0.01
63	0.02	0.21	0.00	0.01	0.00
80	-0.39	-4.16	-0.02	-0.20	-0.03
100	0.21	2.27	0.01	0.11	0.02
125	0.40	4.28	0.02	0.20	0.03
160	0.73	7.83	0.03	0.37	0.06
200	1.07	11.53	0.05	0.55	0.09
250	1.56	16.78	0.07	0.80	0.13
315	2.39	25.69	0.11	1.22	0.20
400	2.80	30.12	0.13	1.43	0.24
500	2.92	31.39	0.14	1.49	0.25
630	3.62	38.91	0.17	1.85	0.30
800	4.38	47.12	0.21	2.24	0.37
1000	4.91	52.88	0.23	2.52	0.41
1250	5.81	62.53	0.28	2.98	0.49
1600	6.81	73.26	0.32	3.49	0.57
2000	7.66	82.40	0.36	3.92	0.64
2500	8.34	89.80	0.40	4.28	0.70
3150	8.58	92.40	0.41	4.40	0.72
4000	8.70	93.63	0.41	4.46	0.73
5000	8.95	96.30	0.43	4.59	0.75
6300	9.12	98.15	0.43	4.67	0.77
8000	9.18	98.79	0.44	4.70	0.77
10000	9.30	100.13	0.44	4.77	0.78
12500	9.93	106.90	0.47	5.09	0.84

Test Report**Frasch**
2026-06-16**RAL™-A26-327**
Page 8 of 8**APPENDIX B: Instruments of Traceability**

Specimen: Skinny Baffle (8") in seven rows of three objects each, rows spaced 18" on center, objects in each row spaced 1" apart (See Full Report)

<u>Description</u>	<u>Model</u>	<u>Serial Number</u>	<u>Date of Certification</u>	<u>Calibration Due</u>
System 1	Type 3160-A-042	3160-106968	2025-07-21	2026-07-21
Bruek & Kjaer Mic and Preamp H	Type 4943-B-001	2525859	2025-11-18	2026-11-18
Bruel & Kjaer Pistonphone	Type 4228	2781248	2025-07-21	2026-07-21
EXTECH Hygro 639	SD700	A.103639	2025-12-29	2026-12-29

APPENDIX C: Revisions to Original Test Report

Specimen: Skinny Baffle (8") in seven rows of three objects each, rows spaced 18" on center, objects in each row spaced 1" apart (See Full Report)

<u>Date</u>	<u>Revision</u>
2026-07-10	Original report issued

END